

REPORT

3933 US ROUTE 11 CORTLAND, NEW YORK 13045

Order No. G100766457 Revision Date: October 31, 2012 Original Issue Date: June 30, 2012

REPORT NO. 100766457CRT-001

TEST OF SAFETY GLASSES
MODELS
SPY CLEAR | SPY GREY

RENDERED TO

VICSA SAFETY SA PINTOR CICARELLI 683 8950002 SAN JOAQUIN, CHILE

<u>REVISION NOTE:</u> Changed NEAR UV from scientific notation to standard notation and two decimal places.

DATA REQUESTED

The client requested optical testing to Section 5 of ANSI Z87.1.

AUTHORIZATION

This test service was authorized by signed quote number 500380131.

REFERENCE DOCUMENTS: The following Test Standards were used in part or in total to test

each sample:

ANSI Z87.1 2010 American National Standard for Occupational and Educational

Personal Eye and Face Protection Devices

ASTM D1003 2007 Standard Test Method for Haze and Luminous Transmittance of

Transparent Plastics

DEVICES SUBMITTED

The samples were received by Intertek on June 21, 2012 in undamaged condition, and were tested as received. The sample designations were 250592-01 through 250592-02.

DATES OF TESTS

June 28, 2012 through June 29, 2012



EQUIPMENT LIST

Equipment Used	Model Number	Number	Calibration Date	Due Date	_
Optronics Spectroradiometer	OL750D	E288	06/28/12	06/30/12	
Gardner Hazemeter	XL211	N328	06/28/12	07/28/12	
Extech Hygrothermometer	445703	T1357	10/26/11	10/26/12	
Extech Hygrothermometer	445703	T1355	10/29/11	10/29/12	
Intertek 100ft Goniometer	NA	N060	08/12/11	08/12/12	

TESTS

Section 5.1.1 Optical Quality:

Lenses shall be free of striae, bubbles, waves and other visible defects which would impair their optical quality.

Section 5.1.2 Luminous Transmission:

Clear lenses shall have a luminous transmission of not less than 85%. Clear and Filter lenses shall be labeled in accordance with Table 4a of ANSI Z87.1. Plano and prescription lenses shall comply with Tables 6 - 10 of ANSI Z87.1 where applicable.

Section 5.1.3 Haze:

Clear and plano lenses shall not exhibit more than 3% haze.

Section 5.1.4 Refractive Power, Astigmatism, Resolving Power, Prism and Prism Imbalance:

Lenses shall meet the tolerances for Refractive Power, Astigmatism and Resolving power as specified in Table 1 of ANSI Z87.1. Lenses shall meet the tolerances for Prism and Prism Imbalance as specified in Table 2 of ANSI Z87.1.

Table 1: Tolerance on Refractive Power, Astigmatism and Resolving Power							
Protector Refractive Power		Astigmatism	Resolving Power				
Spectacle	± 0.06 D	≤ 0.06 D	Pattern 20				
Goggle	± 0.06 D	≤ 0.06 D	Pattern 20				
Faceshield Windows	No Requirement	No Requirement	Pattern 20				
Welding Helmet Lenses	± 0.06 D	≤ 0.06 D	Pattern 20				

Table 2: Tolerance on Prism and Prism Imbalance							
Protector	Prism	Vertical Base In Imbalance		Base Out Imbalance			
Spectacle	≤ 0.50 ∆	≤ 0.25 ∆	≤ 0.25 ∆	≤ 0.50 ∆			
Goggle	≤ 0.25 ∆	≤ 0.125 ∆	≤ 0.125 ∆	≤ 0.50 ∆			
Faceshields	≤ 0.37 ∆	≤ 0.37 ∆	≤ 0.125 ∆	≤ 0.75 ∆			
Welding Lenses	≤ 0.50 ∆	≤ 0.25 ∆	≤ 0.25 ∆	≤ 0.75 ∆			



RESULTS OF TEST

Section	511	Ontical	Quality:
Section	O. I. I	Optical	Quality.

Control Number	Model Number	Defects	Notes	Pass/Fail
250592	Clear	None		Pass
250592	Grey	None		Pass

Section 5.1.2 Luminous Transmission:

		Percent Tra		
Control Number	Model Number	Left Eye	Right Eye	Pass/Fail/NA
250592	Clear	91.6	91.6	Pass
250592	Grey	9.93	10.5	NA

Section 5.1.3 Haze:

		Percent		
Control Number	Model Number	Left Eye	Right Eye	Pass/Fail/NA
250592	Clear	0.68	0.68	Pass
250592	Grev	0.52	0.40	Pass

Section 5.1.4 Refractive Power, Astigmatism, Resolving Power

Control Number	Model Number	Eye	Refractive Power (diopeters)	Astigmatism (diopeters)	Resolving Power	Pass/Fail
250592	Clear	Left Right	0.03 0.03	0.04 0.04	48 48	Pass
250592	Grey	Left Right	0.03 0.02	0.05 0.05	48 48	Pass

Section 5.1.4 Prism and Prism Imbalance

Control Number	Model Number	Eye	Prism (Δ)	Vertical Imbalance (Δ)	Base in Imbalance (Δ)	Base Out Imbalance (Δ)	Pass/Fail
250592	Clear	Left Right	0.18 0.23	0.06	0.00	0.00	Pass
250592	Grey	Left Riaht	0.18 0.14	0.00		0.06	Pass

Transmittance Ratings

	Control	Model		Visible Light Transmittance		UV Transm	JV Transmittance (%)		
	Number	Number	Eye	(%)	L-Scale	Far UV	Near UV	U-Scale	
-	250592	Clear	Left Right	91.6 91.6	Clear	0.00	0.00	U6	•
	250592	Grey	Left Right	9.93 10.5	L3	0.00	0.00	U6	



PHOTO OF SAMPLE(S):

SPY CLEAR



SPY GREY



In Charge Of Tests:

Denis Niggli Engineer Lighting Division

Attachment: None

Report Reviewed By:

David Ellis

Senior Project Engineer

Lighting Division